



White Petroleum Jelly

METHOD	VALUE/RESULTS	PROPERTIES
Kinematic Viscosity @ 100°C	6 cst	ASTM D445
Congealing Point	55.2°C	ASTM D938
Penetration	More than 125 (0.1 mm)	ASTM D1321
Color (Lovibond)	0.5-0.7 y	IP-17 METHOD A 2" CELL
Acidity or Alkalinity	According to the test method	B.P 2007
Drop Melting Point	58°C	ASTM D127
Sulphated Ash	Less than 0.05%	B.P 2010
Flash Point	210°C Min.	ASTM D92
Odor	Odorless	—