



Fully Refined Paraffin Wax (Less 1%)

Oil Content	Less 1%	ASTM D721
Congealing Point	57°C	ASTM D938
Odor	Odorless	BP 2015
Specific Gravity at 25°C	0.81-0.85 g/cm³	ASTM D1298
Color	White 0.1 Yellow	BP 2015 Lovibond IP 17 Method A 2 cell
Melting Point	58-60°C	ASTM D127
Flash Point	220-245°C	ASTM D92