



Slack Wax Light

Color	Max 1.5%	BP 2015
Congeaing Point	54°C	ASTM D938
Specific Gravity at 25°C	0.8436 g/cm ³	----
Kinematic Viscosity at 100C	3.98 cst	ASTM D445
Oil Content	10-15%	ASTM D721
Flash Point	206°C	ASTM D92